

XP-002213520

AN - 1985-161558 [27]

AP - JP19830197946 19831022; JP19830197946 19831022; [Previous Publ. J60090853]

CPY - FURU

- NITE

DC - L01 P81

FS - CPI;GMPI

IC - C03B37/02 ; C03B37/023 ; C03C23/00 ; C03C25/00 ; C03C25/02 ; G02B6/00 ; G02B6/44

MC - L01-F03 L01-L05

PA - (FURU) FURUKAWA ELECTRIC CO LTD

- (NITE) NIPPON TELEGRAPH & TELEPHONE CORP

PN - JP60090853 A 19850522 DW198527 005pp

- JP2542356B2 B2 19961009 DW199645 C03C25/02 004pp

PR - JP19830197946 19831022

XA - C1985-070560

XIC - C03B-037/02 ; C03B-037/023 ; C03C-023/00 ; C03C-025/00 ; C03C-025/02 ; G02B-006/00 ; G02B-006/44

XP - N1985-121759

AB - J60090853 Optical glass product e.g. porous glass soot preform, transparent glass preform and optical fibre etc. is improved in radio-active rays resistance by treating it in a H₂-bearing atmos. at elevated temp.

- (50 deg.C or higher of Hydrogen is diffused into the optical glass prod. and bound to defective part of product e.g. O etc. to form OH radical, so that the defective part is removed and excellent radio-active rays resistance is achieved. The higher the treating temp. under H₂-bearing atmos., the shorter the treating time and the stronger the binding strength of OH radical to the defective part. The treatment temp. is pref. kept at 100 - 250 deg.C to prevent damage to primary coatings.

- ADVANTAGE - OH radical is thoroughly and effectively contained in the inside of the optical glass product so as to be improved in radioactive rays resistance without any devitrification.(0/0)

IW - MANUFACTURE RADIATE RESISTANCE OPTICAL PREFORM FIBRE HEAT TREAT HYDROGEN CONTAIN ATMOSPHERE

IKW - MANUFACTURE RADIATE RESISTANCE OPTICAL PREFORM FIBRE HEAT TREAT HYDROGEN CONTAIN ATMOSPHERE

NC - 001

OPD - 1983-10-22

ORD - 1985-05-22

PAW - (FURU) FURUKAWA ELECTRIC CO LTD

- (NITE) NIPPON TELEGRAPH & TELEPHONE CORP

TI - Mfg. radiation-resistant optical preform or fibre - by heat treatment in hydrogen-contg. atmos.

BEST AVAILABLE COPY